



VSS EMULTECH

W. Sacramento, CA 95691
 3785 Channel Drive
 Ph: (916) 371-8480
 Fx: (916) 371-2457

Redding, CA 66001
 7200 Pit Road
 Ph: (530) 241-1364
 Fx: (530) 246-2912

Bakersfield, CA 93308
 3800 Gilmore Avenue
 Ph: (661) 323-5904
 Fx: (661) 323-2737

Product Data Sheet CRS-2h

Tests	ASTM Method	Typical	Specification	
			min	max
Viscosity @ 122°F, SFs	D7496	160.0	75	350
Sieve, %	D6933	0.04	-	0.30
Residue by Distillation, %	D6997	67	65.0	-
Storage Stability, 1 day, %	D6930	0.1		1.0
Demulsibility, %	D6936	65.0	40.0	
Particle Charge	D7402	Positive	Positive	
Tests on Residue				
Oil Disitlate, Vol. of Emulsion, %	D6997	0		3
Penetration @ 77°F, 100 g, 5 sec	D5	50	40	90
Ductility @ 77°F, cm	D113	65+	40	-
Solubility in TCE, %	D2042	99.98	97.5	-