



VSS EMULTECH

W. Sacramento, CA 95691
3785 Channel Drive
Ph: (916) 371-8480
Fx: (916) 371-2457

Redding, CA 66001
7200 Pit Road
Ph: (530) 241-1364
Fx: (530) 246-2912

Bakersfield, CA 93308
3800 Gilmore Avenue
Ph: (661) 323-5904
Fx: (661) 323-2737

PRODUCT DATA SHEET SS-1h

Tests		Typical	Specification	
			min	max
Viscosity @ 122°F, SSF	AASHTO T59	20.0	20	100
Sieve, %	AASHTO T59	0	-	0.10
Storage Stability 24hr., %	AASHTO T59	0.2	-	1
Residue by Evaporation, % by mass	AASHTO T59	63.0	57.0	-
Tests on Residue				
Penetration @ 77°F, 100 g, 5 sec	AASHTO T49	52	40	90
Solubility, %	AASHTO T44	99.95	97.5	-