



VSS EMULTECH

W. Sacramento, CA 95691
 3785 Channel Drive
 Ph: (916) 371-8480
 Fx: (916) 371-2457

Redding, CA 66001
 7200 Pit Road
 Ph: (530) 241-1364
 Fx: (530) 246-2912

Bakersfield, CA 93308
 3800 Gilmore Avenue
 Ph: (661) 323-5904
 Fx: (661) 323-2737

Product Data Sheet PMCQS-1h

Tests	Result	Test Method	Specification	
			min	max
Viscosity @ 25°C, SFs	30.0	AASHTO T59	15	90
Sieve, %	0	AASHTO T59	-	0.30
Residue by Evaporation, % by wt	64	AASHTO T59	62.0	-
Settlement, 5 day (%)	0.3	ASTM D244	-	5.0
Particle Charge	Positive		Positive	
Tests on Residue				
Penetration @ 25°C, 100g, 5sec	50	AASHTO T49	40	90
Torsional Recovery, %	32	CA Test 332	20	
Softening Point, 25°C	59	AASHTO T53	57	